



Technical data sheet

IGP-RAPID®complete 881TA-R2

Deep matte, highly reactive polyester single-coat powder coating with a fine texture and optimised robustness, specially developed for temperature-sensitive substrates.



Characteristics

- Deep matte
- Fine texture
- Uni, without effect
- Indoor quality
- More robust & pliable



Material approvals

- [EPD IGP-RAPIDcomplete 88](#)



Powder properties

Particle size:	< 100 µm
Solids:	> 99 %
Density:	1.3 kg/l-1.6 kg/l
Suitability for storage:	min. 9 months at ≤ 15 °C min. 12 months at ≤ 5 °C in an unopened original container
Color tones:	On request



Processing

Pre-treatment

If the surface finish of the MDF ex-works does not meet the quality requirements of the end product, the surface has to be sanded. This will ensure that the material has an evenly smooth surface and is free of any contaminants, minor scratches, dust, grease, etc. For more information, see IGP-TI 111.

Coating devices

All conventional electrostatic systems with corona charging.

For the construction and operation of powder coating plants, the following regulations must be complied with: ATEX RL 2014/34/EU, EN 50177, DIN EN 16985.


Recommended film thickness

100 µm - 140 µm

A homogeneous coating result with textured paints or colour or article-specific differences in hiding power may require higher Film thicknesses. The corresponding processing guidelines must be observed.

For a preliminary calculation of the required powder coating quantity, the required Film thickness must be determined for each specific article.

Curing conditions



T Object	t min	t max
125 °C	5 minutes	9 minutes
130 °C	3 minutes	7 minutes
140 °C	2 minutes	5 minutes

Due to the limited thermal conductivity, the use of infrared- (electric / gas catalytic) or convectional - infrared combined ovens is recommended.

In order to determine ideal curing conditions, we recommend practical trials with the respective object and curing oven.

The curing conditions must be carefully controlled. Powder coatings cured outside the curing window may show deficiencies in the film flexibility. Our technical customer service will advise you.

Application

For optimal coating and surface quality, please follow the recommendations in technical information TI111

Reclaimability

Small portions of recycled powder can be added, automatically if possible, to the fresh powder. Important: Keep overspray to an absolute minimum.



Film properties

Tested on

Substrate: EGGER MBP-L 25mm
Film thickness: 110 µm - 130 µm
Object temperature: 130 °C, 3 min.

Mechanical tests

Hinge Hole Test	≤ 1.1	IGP AA341.42
-----------------	-------	--------------

Chemical tests

Acetone test	10N Level 2	IGP AA341.44
--------------	-------------	--------------

Additional properties

Behavior at chemical influence	C	DIN 68861 - 1 2011-01
Behavior at abrasion	B	DIN 68861 - 2 2020-07
Behaviour at scratches	B	DIN 68861 - 4 2013-02
Behaviour subjection to dry heat	C	DIN 68861-7 1985-04



Further information

Packaging

20 kg cardboard box with inserted antistatic PE liner

Overcoating suitability

For repainting slight sanding is necessary.

Protection of coated parts

Coated parts should be packed after cooling with suitable materials without plasticizers. They should be stored protected from the weather to avoid the formation of condensation and thus water spots on the coating.

Cleaning

The coated parts must be cleaned according to the directives RAL-GZ 632 or SZFF 61.01.

Paint removal and disposal

After use, coated goods should be supplied to the normal recycling process. The disposal methods for sludges or residual powders must be observed in accordance with the local official provisions whilst taking Waste Code "080201 Coating Powder Wastes" in accordance with the European Waste Catalogue into consideration.

This application-related advice is given to the best of our knowledge. However, this information is non-obligatory and does not exempt you from carrying out your own tests. Application, use and processing of these products are beyond our control and are therefore on your responsibility.

Consult the Safety Data Sheet prior to use. Article-specific safety data sheet and comprehensive risk management measures available at: [igp-powder.com](https://www.igp-powder.com)